

411 Tintable Primers



Tintable Primer 1




411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE	100,00	116,80	292,00	584,00	1168,00
411 GREY					
411 DARK GREY					
411 BLACK					
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 2



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE	60,00	77,87	194,67	389,33	778,67
411 GREY	30,00	38,07	95,17	190,33	380,67
411 DARK GREY					
411 BLACK					
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 3



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE					
411 GREY	100,00	114,20	285,50	571,00	1142,00
411 DARK GREY					
411 BLACK					
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 4



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE					
411 GREY	100,00	103,82	259,55	519,09	1038,18
411 DARK GREY					
411 BLACK	10,00	10,25	25,61	51,23	102,45
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 5



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE					
411 GREY	80,00	91,36	228,40	456,80	913,60
411 DARK GREY					
411 BLACK	20,00	22,54	56,35	112,70	225,40
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 6



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE					
411 GREY	50,00	57,10	142,75	285,50	571,00
411 DARK GREY					
411 BLACK	50,00	56,35	140,88	281,75	563,50
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 7



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE					
411 GREY					
411 DARK GREY	100,00	113,50	283,75	567,50	1135,00
411 BLACK					
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75

Tintable Primer 8



411 WET ON WET PRIMER	SHADE RATIO (gr)	100ml (Part A)	250ml (Part A)	500ml (Part A)	1L (Part A)
411 WHITE					
411 GREY					
411 DARK GREY					
411 BLACK	100,00	112,70	281,75	563,50	1127,00
HARDENER 720		23,53	58,81	117,63	235,25
THINNER NORMAL 740/741 SLOW		21,88	54,69	109,38	218,75